

Amendments to the Specification

Please replace the paragraph beginning at page 15, line 11, with the following rewritten paragraph:

The core sheet included bleached chemical pulps from the kraft pulping process, including both hardwood and softwood fiber types. Yellow dye was added to the core at about 1.9 ounces/ton. The yellow dye was ~~CARTOSOL~~ CARTASOL[®] Yellow 3GF supplied by Clariant Corporation (Muttens, Switzerland).